

Technical Datasheet:

PC 41-020

2K-PUR Coating



PC 41-020

is a 2-component, solvent-free, polyurethane coating. This product is suitable for application to rubber mats and situ applied rubber surfaces in order to fill and smooth and level the surface.

Density	@ 23 °C	1,35 g/cm ³
Viscosity	@ 20 °C	thixotrop
Mixing ratio	Part A : Part B (by weight)	100 : 22
Pot life	@ 23 °C; 50 % relative humidity	40 minutes
Touch Dry	@ 23 °C; 50 % relative humidity	12 hours
Tack Free	@ 23 °C; 50 % relative humidity	Over night
Processing temperature		min. 10 °C – 30°C (3°C above dew point)

Installation guidelines

Mix the two components of PC 41-020 by adding the B component to the A component and mixing for a minimum of three minutes. The material should then be poured in to a separate clean container and mixed for a further 1 minute.

Apply PC 41-020 to the substrate using a hand trowel or rubber squeegee

Consumption: approx. 0,6 - 0,8 kg / m²

Safety guidelines

Never use PC 11-028 near flames or open light. Smoking is also strictly prohibited during the application process. Wear approved eye protection and gloves during application. Adequate ventilation or use of a respirator is required in enclosed spaces.

Packaging

Part A: 20,5 kg pail

Part B: 4,5 kg pail

Storage

Store PC 21-025 in a dry and cool place but not below 10 °C. Shelf life of product stored in original unopened containers is 6 months.